

Component - Plastics

E41871

BASF SE

ENGINEERING PLASTICS EUROPE, E-KTE/MP - F206, LUDWIGSHAFEN 67056 DE

368R, 358N, 378P, 388S

Styrene Acrylonitrile (SAN), "Luran", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI		
					Elec	Imp	Str
ALL	1.5	HB	3	0	50	50	50
	2.8	HB	3	0	50	50	50
	6.0	HB	2	0	50	50	50

Comparative Tracking Index (CTI): **1**Dimensional Stability (%): **0**High-Voltage Arc Tracking Rate
(HVTR): **0**High Volt, Low Current Arc Resis (D495): **5**Dielectric Strength (kV/mm): **32**Volume Resistivity (10^x ohm-cm) : **15**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1977-10-28
Last Revised: 2003-10-24

Underwriters Laboratories Inc®

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
			2.8	HB75 (ALL)
			6.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

Underwriters Laboratories Inc®